



Preface

MASTERFORMAT:
Issued:

06 05 23.07
2007-08-21

Metal Truss Connector Plates

Scope

These Evaluation Listings apply to light metal plate connectors used in structural lumber assemblies. The proponent has demonstrated that the product meets the requirements of the following Standard:

- CAN/CSA-O86-01, “Engineering Design in Wood,” (including Supplement CAN/CSA-O86S1-05).

The design values for the metal truss connector plates are based on test results obtained in accordance with CAN/CSA-S347-99 (R2004), “Method of Test for Evaluation of Truss Plates Used in Lumber Joints.”

Standards

CAN/CSA-S347 requires the following tests:

1. Lateral resistance of teeth;
2. Tensile strength of plate;
3. Shear strength of plate; and
4. Ultimate tensile strength of plate material.

Clause 10.8 of CAN/CSA-O86 does not apply to situations where corrosive conditions exist, or in lumber that has been treated with a fire retardant and that is used in wet service conditions or in locations prone to condensation.

- Truss plates shall be manufactured from galvanized sheet steel and should be of G90 coating class meeting Clause 10.8.1.3 of CAN/CSA-O86.

National Building Code of Canada (NBC)

NBC References

The CAN/CSA-O86-01 standard is referenced in the NBC 2005, Division B, Table 4.1.8.9. and Sentence 4.3.1.1.(1).

The CAN/CSA-S347-99 (R2004) standard is not directly referenced in the NBC 2005, however it is referenced in CAN/CSA-O86-01 in Clauses 10.8.1.9, 10.8.3.2.1, and 10.8.4.2.



**Evaluation Listing
CCMC 12182-L**

MASTERFORMAT: 06 05 23.07
 Issued: 1990-10-31
 Re-evaluated: 2012-05-03
 Re-evaluation due: 2014-10-31

Alpine HS20 Truss Plate

1. Evaluation

Conforms to CSA S347-99 (R2004), and CAN/CSA-O86-01 Consolidation (R2006).

2. Description

A galvanized, high-strength low-alloy (HSLA) I410 or II410 steel struss connector plate that is 0.91 mm thick and stamped with 0.0108 teeth/mm² that are 8.5 mm long.

Ultimate tensile strength of plate

Ultimate Tensile Strength (MPa)	Plate Thickness (mm)	Mean Ultimate Strength (MPa)	Correction Factor
480	0.91	520	0.923

Lateral resistance of teeth

Direction of Load	Limit States Design	
	Ultimate Lateral Resistance, n_u	Lateral Slip Resistance, n_s
Units	MPa/Plate	MPa/Plate
Type of Press	Hydraulic	Hydraulic
Species of Wood	S-P-F	S-P-F
Load parallel to grain, plate length parallel to load	1.82	2.45
Load parallel to grain, plate length perpendicular to load	1.26	1.73
Load perpendicular to grain, plate length parallel to load	1.25	1.38
Load perpendicular to grain, plate length perpendicular to load	1.43	1.85

Tensile strength of plate

Limit States Design	
Direction of Load	Tensile Resistance, t_p
Units	N/mm/Plate
Plate length parallel to load	301
Plate length perpendicular to load	124

Shear strength of plate

Angle (degree)	Limit States Design	Failure Mode	
	Shear Resistance, v_p (N/mm/Plate)	Shear Failure in T or C	Slots in Plate Axis Two-Joint Plate
0	133	N/A	⊥
30	147	T	//
30	114	C	⊥
60	234	T	//
60	73	C	⊥
90	119	N/A	//
120	90	T	⊥
120	125	C	//
150	116	T	⊥
150	95	C	//

⊥: Slots perpendicular to plate, long dimension

//: Slots parallel to plate long, dimension

C: Compression

T: Tension

N/A: not applicable

3. Standard and Regulatory Information

See the [Preface](#) and the standard for explanation.

Listing Holder: Alpine Systems Corporation
 1701 Creditstone Road
 Concord, ON L4K 5V6
 Tel: 905-417-2766
 Fax: 866-802-4919

Plant(s): Litchfield, IL, U.S.A.
 Sacramento, CA, U.S.A.

This Listing is issued by the Canadian Construction Materials Centre, a program of the Institute for Research in Construction at the National Research Council of Canada. The Listing must be read in the context of the entire CCMC Registry of Product Evaluations.

Readers must confirm that the Listing is current and has not been withdrawn or superseded by a later issue. Please refer to <http://www.nrc-cnrc.gc.ca/eng/services/irc/ccmc.html>, or contact the Canadian Construction Materials Centre, Institute for Research in Construction, National Research Council of Canada, 1200 Montreal Road, Ottawa, Ontario, K1A 0R6. Telephone (613) 993-6189. Fax (613) 952-0268.

NRC has evaluated the material, product, system or service described herein only for those characteristics stated herein. The information and opinions in this Listing are directed to those who have the appropriate degree of experience to use and apply its contents. This Listing is provided without representation, warranty, or guarantee of any kind, expressed, or implied, and the National Research Council of Canada (NRC) provides no endorsement for any evaluated material, product, system or service described herein. NRC accepts no responsibility whatsoever arising in any way from any and all use and reliance on the information contained in this Listing. NRC is not undertaking to render professional or other services on behalf of any person or entity nor to perform any duty owed by any person or entity to another person or entity.