



Evaluation Listing CCMC 13326-L AS-20 Truss Plate

MasterFormat:	06 05 23.07
Evaluation issued:	2008-08-05
Re-evaluated:	2017-12-14
Revised:	2017-12-21

1. Evaluation

The product conforms to CSA S347-14, “Method of test for evaluation of truss plates used in lumber joints,” and CSA O86-14, “Engineering Design in Wood.” CSA S347 test results are shown in the following tables.

Table 1.1 Ultimate Tensile Strength of the Plate Material

Grade of Steel	Uncoated Nominal Plate Thickness (mm)	Mean Ultimate Tensile Strength (MPa)	Correction Factor
SQ275	0.904	391	0.969

Table 1.2 Lateral Resistance of the Teeth (Hydraulic Press)

Direction of Load	Lateral Resistance (MPa/Plate) Specific Gravity (SG) = 0.42		Lateral Resistance (MPa/Plate) Specific Gravity (SG) = 0.47	
	Ultimate Lateral Resistance n_u	Lateral Slip Resistance n_s	Ultimate Lateral Resistance n_u	Lateral Slip Resistance n_s
Load parallel to grain, plate length parallel to load	2.35	2.16	2.56	2.38
Load parallel to grain, plate length perpendicular to load	2.01	2.07	2.30	2.31
Load perpendicular to grain, plate length parallel to load	1.72	1.70	1.85	1.88
Load perpendicular to grain, plate length perpendicular to load	1.72	1.82	1.86	2.09

Table 1.3 Roller Press Modification Factors

Roller diameter	457 mm (18 in.)	
Roller feed speed	37.3 m/min (122.5 ft./min)	
Ultimate lateral resistance modification factor, K_{pu}	0.74 (SG = 0.42)	0.82 (SG = 0.47)
Slip modification factor, K_{ps}	0.77 (SG = 0.42)	0.83 (SG = 0.47)

Table 1.4 Tensile Strength of Plate

Direction of Load	Unit	Tensile Resistance, t_p
Load parallel to plate length	N/mm/plate	167

Load perpendicular to plate length	N/mm/plate	165
------------------------------------	------------	-----

Table 1.5 Shear Strength of Plate

Angle (Degree)	Shear Resistance, v_p (N/mm/Plate)	Slots in Plate Axis
0, 180	110	⊥
30T	127	∥
30C	99	⊥
60T	151	∥
60C	87	⊥
90	86	∥
120T	100	⊥
120C	90	∥
150T	125	⊥
150C	85	∥

Legend for Table 1.5:

- ⊥ Slots perpendicular to the plate, long dimension
- ∥ Slots parallel to the plate, long dimension
- C Compression
- T Tension

2. Description

The product is manufactured from a 20 ga steel sheet that meets the minimum strength and yield requirements of ASTM A 653/A 653M, “Standard Specification for Steel Sheet, Zinc-Coated (Galvanized) or Zinc-Iron Alloy-Coated (Galvannealed) by the Hot-Dip Process,” Grade SQ275 steel, and galvanized with G90 zinc coating as per ASTM A 924/A 924M, “Standard Specification for General Requirements for Steel Sheet, Metallic-Coated by the Hot-Dip Process.” The product has an uncoated nominal thickness of 0.904 mm and is stamped with 0.0124 teeth per square mm. The teeth are approximately 9.5 mm in length.

3. Standard and Regulatory Information

See the Annex, appended to this Listing, which summarizes the product standard.

This/these product(s) was/were evaluated to the product standard referenced in the Annex current as of 2015-02-03. Note that the Annex may have been updated since this Listing was issued to include more recent editions of the applicable product standard. Therefore, this Listing may not reflect the requirements contained in any updated version of this product standard.

Listing Holder

Simpson Strong-Tie Canada, Limited
 11476 Kingston Street
 Maple Ridge, BC V2X0Y5

Telephone: 604-465-0296

Fax: 604-465-0297

Web site: <http://www.strongtie.com>

Plant(s)

Edenton, NC, USA

Disclaimer

This Listing is issued by the Canadian Construction Materials Centre, a program of NRC Construction at the National Research Council of Canada. The Listing must be read in the context of the entire CCMC Registry of Product Evaluations.

Readers must confirm that the Listing is current and has not been withdrawn or superseded by a later issue. Please refer to http://www.nrc-cnrc.gc.ca/eng/solutions/advisory/ccmc_index.html, or contact the Canadian Construction Materials Centre, NRC Construction, National Research Council of Canada, 1200 Montreal Road, Ottawa, Ontario, K1A 0R6. Telephone 613-993-6189. Fax 613-952-0268.

NRC has evaluated the material, product, system or service described herein only for those characteristics stated herein. The information and opinions in this Listing are directed to those who have the appropriate degree of experience to use and apply its contents. This Listing is provided without representation, warranty, or guarantee of any kind, expressed, or implied, and the National Research Council of Canada (NRC) provides no endorsement for any evaluated material, product, system or service described herein. NRC accepts no responsibility whatsoever arising in any way from any and all use and reliance on the information contained in this Listing. NRC is not undertaking to render professional or other services on behalf of any person or entity nor to perform any duty owed by any person or entity to another person or entity.

Date modified:

2017-12-21